

KRAFT+POLYESTER+KRAFT+PAPER

Sr. No	Cl. No.	Test particulars	Requirement as Per specification	Obtained value	Remarks
1.	2	Total Thickness, mm	-	Central 0.218	-
2.	3	Substance, g/m ²	-	Central 269.53 Maximum 269.74 Minimum 267.13	-
3.	4	Tensile strength and Elongation at break			
	4.3	- Unfolded			
		(i) Tensile strength, N/10mm of width			
		- Machine direction	-	Central 184.2	-
		- Cross direction	-	Central 96.3	-
		(ii) Elongation, %			
		- Machine direction	-	Central: 3.1	-
		- Cross direction	-	Central: 10.6	-
	4.4	- Folded			
		(i) Tensile strength, N/10mm of width			
		- Machine direction	-	Central: 183.8	-
		- Cross direction	-	Central: 93.7	-
4.	9	Electric strength, ac in air at 27°C Breakdown voltage, kV			
		- Unfolded	-	Central 10.0	-
		- Folded	-	Central: 7.3	-